

ALPHA® FT-2002 ROSIN FREE

Colophony Free, Halide Free, No Clean, Flux Cored Wire Solder

DESCRIPTION

ALPHA FT-2002 Rosin Free is a fully synthetic (no rosin or rosin derivatives) flux cored wire solder. It is designed to be a direct replacement for traditional rosin-cored wire solders. The flux core is also halide-free yet still provides very good wetting performance.

ALPHA FT-2002 Rosin Free leaves post-soldering minimal residues that are clear and hard. Residues have a high surface insulation resistance and can be left without need to remove them.

ALPHA FT-2002 Rosin Free has been formulated to have a distinctive odor that distinguishes it from rosin containing flux cored wire solders.

FEATURES & BENEFITS

- *Rosin Free* → *Colophony Free for a safe working environment*
- *Halide Free* → *High Electrical Reliability*
- *Fast wetting* → *Low Cycle times for component touch-up and manual assembly*
- *Good spread characteristics* → *Excellent First Pass Solder Joints.*
- *Minimal, clear & safe residue* → *No-Clean Residues, Useful for all Applications*
- *Provides good joint appearance* → *Makes Inspection easy*

ALPHA FT-2002 Rosin Free suitable for use in any commercial no-clean hand soldering application that requires a rosin free product and compliance to J-STD-004 – ORL0 classification.

PRODUCT INFORMATION

Standard	Alloy Designation	Melting or Solidus / Liquidus Temp °C	Flux Amount
J-STD-006C	SAC305	217 - 221	1.4% & 2.2%
ISO 9453	Sn63/Pb37	183	1.4%
ISO 9453	Sn60/Pb40	183 - 191	1.4%

* **ALPHA FT-2002** Rosin Free may also available in other alloys and flux amounts on request.

APPLICATION

A soldered joint is formed by heating the parts to be soldered to a temperature in excess of the melting point of the alloy to be used – in hand soldering this is how a soldering iron is used. By feeding the cored wire onto the parts, the flux is able to flow and remove oxidized metal, while the solder creates a thin inter-metallic bond which becomes the solder joint.



ALPHA® FT-2002 ROSIN FREE

Colophony Free, Halide Free, No Clean, Flux Cored Wire Solder

Note the following tips:

- Use a soldering iron tip size and form to suit the operation: small tips for soldering large components may prevent the formation of a joint or slow the process down.
- Select a solder wire diameter to suit both the soldering iron tip and the parts/components to be soldered.
- Soldering iron systems should provide sufficient heat to satisfy the requirements of the points above.
- A typical solder tip temperature would be between 120°C and 160°C above the liquidus temperature of the alloy. The ideal temperature to use is dependent on how thermally demanding the assembly is.
- Cored solder wires can be provided in different grades of alloy so always ensures that you have selected the right grade for the application.
- Do not overheat as this causes an increase in the depth of the inter-metallic layer, which in turn weakens the joint.

If you choose to use a liquid rework flux, **ALPHA NR205** No-Clean Low Residue Flux is recommended to maintain high electrical reliability. **ALPHA NR205** is available in Alpha's Write Flux Pens for precision flux application.

TECHNICAL DATA

Physical Properties	Typical Values
Acid Value:	250 mg KOH/g flux (IPC-TM-650-2.3.13)
Halide Content:	<500 ppm (IPC-TM-650-2.3.28.1)
Classification:	ORL0 per IPC J-STD-004

Electrical Reliability Test	Requirements	Results
IPC SIR Testing (J-STD-004A)	$1.0 \times 10^8 \Omega$ minimum	PASS

Chemical Reliability Test	Requirements	Results
Copper Mirror Test (IPC-TM-650- 2.3.32)	No complete removal of copper	PASS
Copper Corrosion Test IPC-TM-650-2.6.15	No evidence of corrosion	PASS

SAFETY

Please refer to the Safety Data Sheet as the primary source of health and safety information. The most recent version of the SDS is available from AlphaAssembly.com.

Observe standard precautions for handling and use. Use in well ventilated areas. DO NOT SMOKE during use.

ALPHA FT-2002 Rosin Free wire is not considered toxic. However, its use in typical soldering applications will generate a small amount of decomposition and fumes. These fumes should be adequately exhausted / vented for operator safety and comfort.

ALPHA® FT-2002 ROSIN FREE

Colophony Free, Halide Free, No Clean, Flux Cored Wire Solder

STORAGE

ALPHA Cored Solder Wires should be stored in dry conditions and within a temperature range of 0°C to 40°C. Alpha guarantees the product shelf life for three years from the date of manufacture when stored in the recommended conditions.

CONTACT INFORMATION

To confirm this is the most recent issue, please contact Alpha Assembly Solutions
AlphaAssembly.com

North America
300 Atrium Drive
Somerset, NJ 08873, USA
800.367.5460

Europe
Unit 2, Genesis Business Park
Albert Drive
Woking, Surrey, GU21 5RW, UK
01483.758400

Asia
8/F., Paul Y. Centre
51 Hung To Road
Kwun Tong, Kowloon, Hong Kong
852.3190.3100

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency directory assistance Chemtrec 1 - 800 - 424 - 9300.

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OR MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect and consequential damages that may result from use of the products under conditions, and agrees to exonerate, indemnify and hold harmless MacDermid Incorporated therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in infringement of any patent rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

® Registered Trademark of MacDermid Performance Solutions. ™ Trademark of MacDermid Performance Solutions.
© Platform Specialty Products Corporation and its subsidiaries 2016.