

ALPHA® SLS 65C Series

No-Clean Flux

DESCRIPTION

ALPHA SLS 65C was specifically developed to eliminate the tendency for solder balling and solder bridging-two defects which are normally associated with the use of the chip wave. Of all low solids (< 4% solids), no-clean fluxes, SLS 65C exhibits the lowest tendency for solder ball generation over a wide variety of solder masks. SLS 65C should be considered for use by any assembler who has board designs which are sensitive to solder bridging, performs pin testing, and whose specification requires an extremely low frequency of solder balls.

ALPHA SLS 65C is an active, low solids, no-clean flux. It is formulated with a proprietary mixture of organic activators. Several proprietary additives are formulated into **ALPHA SLS 65C** which acts to reduce the surface tension between the solder mask and the solder; thereby, dramatically reducing the tendency of solder ball generation. The formulation of **ALPHA SLS 65C** is also designed to be more thermally stable; thereby, reducing the occurrence of solder bridging.

The standard solids content for **ALPHA SLS 65C** is 2.2%. Where use of a lower solids flux is appropriate, the solids content extends down to 1.6% solids for **ALPHA SLS 65C-1.6**. This provides the user better board cosmetics.

FEATURES & BENEFITS

- Thermally stable activators provide the lowest solder bridging in a low solids, no-clean flux.
- Reduces the surface tension between solder mask and solder to provide the lowest solder ball frequency of any low solids, no-clean flux.
- Very low level of non-tacky residue to reduce interference with pin testing and exhibit no visible residue.
- Cleaning is not required which reduces operating costs.
- Bellcore-Compliant for long term electrical reliability.

APPLICATION

PREPARATION - In order to maintain consistent soldering performance and electrical reliability, it is important to begin the process with circuit boards and components that meet established requirements for solderability and ionic cleanliness. It is suggested that assemblers establish specifications on these items with their suppliers and that suppliers provide Certificates of Analysis with shipments and/or assemblers perform incoming inspection. A common specification for the ionic cleanliness of incoming boards and components is 5µg/in² maximum, as measured by an Omegameter with heated solution.

Care should be taken in handling the circuit boards throughout the process. Boards should always be held at the edges. The use of clean, lint-free gloves is also recommended. When switching from one flux to another, the use of a new foam stone is recommended (for foam fluxing).

Conveyors, fingers and pallets should be cleaned. **ALPHA SM-110** Solvent Cleaner has been found to be very useful for these cleaning applications. When foam fluxing, do not use hot fixtures or pallets. Hot fixtures/pallets will deteriorate the foam head.

ALPHA® SLS 65C Series

No-Clean Flux

FLUX APPLICATION – ALPHA SLS 65C is formulated to be applied by foam, wave or spray methods. When foam fluxing, the foam fluxer should be supplied with compressed air which is free of oil and water. Keep the flux tank full at all times. The flux level should be maintained 1 inch to 1-½ inches above the top of the stone. Adjust the air pressure to produce the optimum foam height with a fine, uniform foam head.

A uniform coating of flux is essential to successful soldering. When using the foam or wave method of application, an air knife is recommended after the fluxing operation. An air knife will help ensure that the flux is uniformly distributed across the board and will remove the excess flux. When spray fluxing, the uniformity of the coating can be visually checked by running a piece of cardboard over the spray fluxer or by processing a board-sized piece of tempered glass through the spray and then through the preheat section.

OPERATING PARAMETER	TYPICAL LEVEL
Amount of Flux Applied	Foam, Wave: 300 - 450 µg/cm ² of solids Spray: 200 - 300 µg/cm ² of solids
When foam fluxing Foam Stone Pore Size	20 - 50 µm
Distance that top of stone is submerged below flux	1 - 1½ inches (25 - 40 mm)
Foam Fluxer Chimney Opening	3/8 - 1/2 inch (10 -13 mm)
When foam fluxing, use an Air Knife Air Knife Hole Diameter	1 - 1.5 mm
Distance Between Holes	4 - 5 mm
Distance from Fluxer to Air Knife	4 - 6 inches (10 -15 cm)
Air Knife Angle Back toward Fluxer from Perpendicular	3° - 5°
Topside Preheat Temperature	210°F - 250°F (100 to 120°C)
Bottomside Preheat Temperature	0 to 71.6°F (0 to 22°C) higher than topside
Maximum Ramp Rate of Topside Temperature (to avoid component damage)	2°C/second (3.5°F/second) maximum
Conveyor Angle	5° - 8° (6° most common)
Conveyor Speed	1.3 - 6.0 feet/minute (0.4 - 1.8 meters/min)
Contact Time in the Solder (includes Chip Wave & Primary Wave)	3 - 10 seconds (5 - 7 seconds most common)
Solder Pot Temperature	460 - 500°F (235 - 260°C) for 63Sn/37Pb 491 - 518°F (255 - 270°C) for Lead-free
These are general guidelines which have proven to yield excellent results; however, depending upon your equipment, components, and circuit boards, your optimal settings may be different. In order to optimize your process, it is recommended to perform a designed experiment, optimizing the most important variables (amount of flux applied, conveyor speed, topside preheat temperature, solder pot temperature and board orientation).	

FLUX SOLIDS CONTROL - If foam, wave, or rotary drum spray fluxing, the flux solids will need to be controlled via thinner addition to replace evaporative losses of the flux solvent. As with any flux with less than 5% solids content, specific gravity is **not** an effective measurement for assessing and controlling the solids content. Monitoring and controlling the acid number is recommended for maintaining the solids content. The acid number should be controlled to between 17 and 19. Alpha's Flux Solids Control Kit #3, a digital titrator, is suggested. Request Alpha's Technical Bulletin SM-458 for details on the kit and titration procedure.

When operating the foam fluxer continuously, the acid number should be checked every two to four hours. Over time, debris and contaminants will accumulate in recirculating type flux applicators. For consistent soldering performance, dispose of spent flux every 40 hours of operation. After emptying the flux, the reservoir and foam stone should be thoroughly cleaned with flux thinner.

ALPHA® SLS 65C Series

No-Clean Flux

RESIDUE REMOVAL – ALPHA SLS 65C is a no-clean flux and the residues are designed to be left on the board. However, if desired, ALPHA SLS 65C residues can be removed with ALPHA 2110 Saponifier.

TOUCH-UP/REWORK - Use of the Cleanline Write Flux Applicator with ALPHA NR205 flux and ALPHA Telecore Plus cored solder is recommended for hand soldering applications.

TECHNICAL DATA

Parameters	Typical Values	Parameters/Test Method	Typical Values
Appearance	Clear, colorless liquid	pH (5% aqueous solution)	3.4
Solids Content, wt/wt	2.2%	Recommended Thinner	425 Thinner
Acid Number (mg KOH/g)	18	Shelf Life (from Mfg. Date)	360 days
Specific Gravity @ 25°C (77°F)	0.799 ± 0.003	Container Size Availability	1, 5, and 55 Gal.
Pounds Per Gallon	6.65	Bellcore GR 78-CORE, Issue 1 Compliant	Yes
Flash Point (TCC)	53°F (12°C)	IPC J-STD-004 Designation	ORL0

CORROSION & ELECTRICAL TESTING

CORROSION TEST

Test	Requirement	Results
Silver Chromate Paper	No Detection of Halide	PASS
Copper Mirror Test	No Complete Removal of Copper	PASS
IPC Copper Corrosion Test	No Evidence of Corrosion	PASS

SURFACE INSULATION RESISTANCE(all values in ohms)

Test	Requirement	Results
Bellcore "Comb-Down" – Uncleaned	$> 1.0 \times 10^{11}$	8.8×10^{12}
Bellcore "Comb-Up" – Uncleaned	$> 1.0 \times 10^{11}$	1.4×10^{12}
Bellcore Control Board	$> 2.0 \times 10^{11}$	2.8×10^{13}
IPC J-STD-004 Comb-Down – Uncleaned	$> 1.0 \times 10^8$	5.6×10^9
IPC-J-STD-004 Comb-Up – Uncleaned	$> 1.0 \times 10^8$	2.3×10^9
IPC J-STD-004 Control Board	$> 1.0 \times 10^9$	2.2×10^{10}
Bellcore Test Condition (per GR78-CORE, Issue 1): 35°C/85%RH/ 5 days /-48 volts, measurement @ 100V/25 mil lines/ 50 mil spacing. IPC Test Condition (per J-STD-004): 85°C/85%RH/ 7 days/-50V, measurement @ 100V/IPC B-24 board (0.4mm lines, 0.5mm spacing).		

ALPHA® SLS 65C Series

No-Clean Flux

ELECTROMIGRATION (all values in ohms)

Test Condition	SIR (Initial)	SIR (Final)	Requirement	Result	Visual Result
Bellcore "Comb-Up" Uncleaned	3.4×10^9	1.2×10^{11}	SIR (Initial)/SIR (Final) < 10	Pass	Pass
Bellcore "Comb-Down" Uncleaned	2.1×10^9	1.3×10^{11}	SIR (Initial)/SIR (Final) < 10	Pass	Pass
Bellcore Test Condition (per GR78-CORE, Issue-1): 65°C/85%RH/500 Hours/10V, measurement @ 100V/IPC B-25 B Pattern (12.5 mil lines, 12.5 mil spacing).					

SAFETY

Please refer to the Safety Data Sheet as the primary source of health and safety information. The most recent version of the SDS is available from AlphaAssembly.com.

Inhalation of the flux solvent and volatilized activator fumes that are generated at soldering temperatures may cause headaches, dizziness and nausea. Suitable fume extraction equipment should be used to remove the flux from the work area. An exhaust at the exit end of the wave solder machine may also be needed to completely capture the fumes. Observe precautions during handling and use. Suitable protective clothing should be worn to prevent the material from coming in contact with skin and eyes. **ALPHA SLS 65C** flux contains highly flammable solvent with a flash point of 53°F (12°C). The flux must not be used near open flame or near non-flameproof electrical equipment.

CONTACT INFORMATION

To confirm this is the most recent issue, please contact Alpha Assembly Solutions

AlphaAssembly.com

North America 300 Atrium Drive Somerset, NJ 08873, USA 800.367.5460	Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 01483.758400	Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100
---	--	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency directory assistance Chemtrec 1 - 800 - 424 - 9300.

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OR MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect and consequential damages that may result from use of the products under conditions, and agrees to exonerate, indemnify and hold harmless MacDermid Incorporated therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in infringement of any patent rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© Registered Trademark of MacDermid Performance Solutions.™ Trademark of MacDermid Performance Solutions.
 © Platform Specialty Products Corporation and its subsidiaries 2016.